



## TECHNONICOL 24 WATERPROOFING MASTIC

### Description of material

Waterproofing TECHNOMICOL 24 is a ready-to-use material based on oil bituminous containing process additives, mineral fillers, and solvent.

### Application areas

Application areas for waterproofing TECHNOMICOL 24:

- Surface waterproofing of concrete, wood and other engineering structures (basements, cellars, piles).

### Method of application

Mastic is applied to a processed surface using a paint brush, putty knife or by pouring and levelling using special combs



### Consumption

- for one layer is 1 kg/m<sup>2</sup>.
- It is recommended 2 layers for installation of surface waterproofing.

### Packing

Bucket 3, 10 and 20 liters.

### Storage

Store in a dry place protected against sunlight at a temperature between -20°C and +30°C.  
 Guaranteed storage period - 18 months.

Property	Value
Strength of adhesion to the base, MPa, not less than:	
with concrete	0.1
with metal	0.1
Shear strength of glued bond, kN/m	2.0
Water absorption over the course of 24 h, % by weight	0.4
Mass fraction of non-volatile substances, %	65
Softening temperature, °C	80
Relative viscosity, s	10
Flexibility on R=5.0 ± 0.2 mm beam at -5°C	no cracks
Water resistance for 10 min at pressure 0,03 MPa	withstands