


**PRODUCT TECHNICAL
DATA SHEET**
Nr. 105
16 March 2017
“Zavod Shinglas” LLC
Vostochny Promuzel, 21, Bld. 58
390000, Ryazan, Russia
Phone: (4912) 911-228, 911-221;
Fax: (4912) 911-221; www.shinglas.ru
**CHARACTERISTICS OF THE PRODUCT:
GENERAL INFORMATION**
PRODUCT: TECHNOMICOL Roofing shingles, Quadrille

Produced according to requirements: EN 544:2011. Bitumen shingles with mineral and/or synthetic reinforcements - Product specification and test methods.

MANUFACTURER: “Zavod Shinglas” LLC, Ryazan, Vostochny Promuzel, 21, Bld. 58
ORIGIN: Russian Federation

INTENDED USE: Discontinuously laid roof covering for buildings

 The bitumen shingles are tiled on pitched roofs the inclination of which is $\geq 12^\circ$.

The bitumen shingles are used for installation of the new roofs and reconstruction of the old ones.

METHOD OF APPLICATION: it fastens mechanically to the smooth and continuous basis of pitched roofs with roofing nails according to the manufacturer installation instruction.

TECHNICAL DATA:

Characteristics	Test method in the EN 544:2011 or other standards	Units	Requirements	Value or statement	Declared tolerances
Mass of bitumen	6.2	g/m ²	≥ 1300	1350	± 50
Height (H)	6.3	mm	minimum 250	317	$\pm 3,0$
Width (W)	6.3	mm	maximum 1200	1000	$\pm 3,0$
Flow resistance at elevated temperature	EN 1110	mm	≤ 2 mm at 110 °C	Pass	
Adhesion of granules and flakes of slate	EN 12039	g	$\leq 2,5$	$\leq 1,2$	
External fire performance	ENV 1187	–	In accordance with EN 13501-5	B _{ROOF} (t1)	
Reaction to fire	EN 13501-1	–	EN 13501-1	E	

PACKING DATA:

Main characteristics	Units	QUADRILLE roofing shingles
Package	m ²	3,0
Weight of package	kg.	25,20
Quantity in the package	units	22
Quantity on the pallet	m ²	108
Weight of a pallet, gross weight	kg.	932

REFERENCES OF MANUFACTURER:

Packages with shingles should be stored in horizontal position combined on wooden pallets no more than 12 rows of packages in height and should be protected against moisture, heat (temperature not higher than +40°C) and mechanical damage. The minimum temperature of installation is 6 °C. In the cold season, the Packages with shingles should be kept at the temperature more than +20°C not less 24 hours before use. Storage life before installing 18 m.